



1000HS – Clear Top Coat HS

Product Description

High quality 2K Clear for panel repair and overall resprays. Good filling properties, excellent gloss and flow in combination with very good polishability. It is extremely stable when applied on vertical surfaces and it can be overcoated within 24 h without intermediate sanding.

Suitable Substrates

- GenRock basecoat

Product Application



	100% Clear	50% Hardener	5-10% Thinner
1000HS		H555 FAST	S719 FAST S711 NORMAL S721 SLOW
		H666 NORMAL	
		H777 SLOW	
		H444 SUPER FAST	



16-18 sec / DIN 4 mm / 20 °C (68 °F)
Pot life 5h at 20°C



HVLP 1.3 – 1.5 mm (2 spray passes)
2.0 - 2.5 bar inlet pressure



2 coats: 50 - 60 microns



Wait 10 min before increasing temperature
Low bake 20 min at 60°C panel temperature

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.



1000HS – Clear Top Coat HS



Short Wave 8 min
The object should be maintained at greater than 60cm from source.



Wear suitable protection

Product Characteristics

Specific Gravity: 0.985 kg/cm³

Flash Point: 25°C (77°F)

Solid Content: 52.1 % by weight

Coverage: 8 - 9 m²/l at 50-micron dry film thickness (theoretical)

SDS: Refer to the Safety Data Sheet

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.