

Description:

A VOC compliant, high build, two component sanding primer surfacer with good vertical stability, good application and filling properties. It is especially easy to sand particularly for hand sanding applications. Direct to plastic with addition of plastic additive 8230.

Suitable Substrates:

- Existing Finishes except TPA
- OEM Primer or EDP, sanded
- "General" Polyester Putties
- Bare metal substrates must be pre-primed with wash primer 9700.
- Other available colors (Grey 9962, Black 9963, White, 9964, Red 9965)

Product Application:



STIR 9960 well before mixing



100% Clear	25% Hardener	5-25% Thinner
9960	9960 Hardener	General Thinner



22-24 sec / DIN 4 mm / 20°C (68°F) Potlife 4 hours / 20°C (68°F)



Compliant 1.6 – 1.8 mm 2.0 – 2.5 bar inlet pressure HVLP 1.7-2.0 mm; maximum 0.7 bar at the air-cap



2-3 coats 60 microns per coat

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.



<u>}</u> †}†	5-6 minutes at 20 oC (68 oF) between coats
	Air dry overnight 30 mn. at 60°C (140°F)
	10 – 15 mn. Short Wave The object should be maintained at greater than 60cm from source
· E	Initial Sanding with P500 - P600 grit Final Sanding with P800 - P1000 grit
	Initial Sanding with P320 grit Final Sanding with P400 - P500 grit
	Clean Surface to remove contamination prior to application of top coat
	GenRock Top Coat GenRock, Gen2O Basecoats
	Wear suitable protection

 $Disclaimer: Users\ assume\ full\ responsibility\ for\ any\ consequences\ resulting\ from\ the\ incorrect\ usage\ of\ our\ products.$





<u>N.B:</u>	solid color has poor op 2K toner into the prime will enhance the color	rs: When the GenMix Pro syster acity, we recommend the follower which will assist you in achie and save on unnecessary coats tep costs to a minimum.	wing: Add the relevant ving a background that
Process:	Using the appropriate primer from our range mix:		
	100% Clear	25% Hardener	5-25% Thinner
	9960	9960 Hardener	General Thinner
	All other processes rea	main the same as per the 9960 d sanding.	TDS sheet on

9960 Primer on Plastics Direct:

With the addition of 8230, 9960 can be applied direct to plastics without the need for a 1k plastic adhesion promotor (plastic primer)



 100% Clear	25% Hardener	5-25% Thinner	15% Plastic Additive
9960	9960 Hardener	General Thinner	8230

All other processes remain the same as per the 9960 TDS sheet on application, drying and sanding.



Potlife 45-60 mins / 20°C (68°F)

Product Characteristics:

VOC(2004/42/EC):	485 g/l (EU limit value for this category IIB.c being max. 540g/l)
Specific Gravity:	1.666 kg/cm3
Flash Point:	25°C (77°F)
Solid Content:	67.8 % by weight – ready to spray

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.





Coverage:	5.7-5.8 m2 /l at 80 micron film thickness (theoretical)
SDS:	Refer to the Safety Data Sheet

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.

