




THINNER TDS



	PARTS	OPAQUE COLORS	BICOAT	CLEAR TOP COAT
30°		S711≈ S811 S721≈ S821	S711≈ S811 S721≈ S821	S721≈ S821
25°		S721≈ S821	S711≈ S811 S721≈ S821	S721≈ S821
20°		S711≈ S811	S719 S721≈S821	S721≈ S821
15°		S711≈ S811	S711≈ S811	S711≈ S811
		S719	S719	S719
		S711≈ S811	S711≈ S811	S711≈ S811

“Use S2050 in temperatures exceeding 30°C

www.generalrefinish.com