



9900 – Universal Primer Grey

Product Description

9900 Universal Primer is a 1k, fast dry, high build and easy to sand surfacer.

Suitable Substrates:

- Old and Sound thermoset topcoats.
- General polyester fillers.

Product Application:



Genclean 8241



100 parts Primebuild
50-150 parts Thinner S711 or G6



HVLP: Nozzle: 1.6 to 2.2 mm



2 -3 Coats

S711 Thinner	Viscosity	Thickness
50%	45"	23 μ film thickness/each coat
100%	18"	15 μ film thickness/ each coat
150%	14"	12 μ film thickness/ each coat



Wait 5 to 10 minutes between each coat.

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.



9900 – Universal Primer Grey



Sandable after 20 to 40 minutes at 20°C for a thickness of 40 to 60 microns



Dry sand with P 320 grit paper



Can be overcoated with all General topcoats except Gen20



Wear suitable protection

Product Characteristics:

VOC(2004/42/EC): 700g/l

Specific Gravity: 1.25 kg/cm³

Flash Point: 20°C (70°F)

Solid Content: 52.3 % by weight pre-dilution

Coverage: 6 m²/l at 20 micron film thickness (theoretical)

SDS: Refer to the Safety Data Sheet

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.