



4206 - Accelero Air dry 2K VOC Dark Grey

Product Description

Accelero 4204 is a VOC High Build Air-Dry 2K Primer with excellent filling properties and sandability. It is recommended for high performance bodyshops focusing on efficiency, space utilization and cost-reduction with no compromise on premium quality.

Accelero 4202 is easy to sand within 1 hour from application at 20oc room temp. It maintains an excellent gloss holdout when top coated with any General top coating material. It uses the same HS hardener family (H500, H600) as other primers in the GENERAL range, providing a complete and compact offer.

Suitable Substrates:

- Old and Sound thermoset topcoats.
- General polyester fillers.
- Sound OEM Gen₂O basecoat

Notes:

- Adhesion promoter is required to apply to special substrate i.e: plastic, fiber glass, and GRP.
- etch primer (9700) is required to apply to bare metal prior to 420X application

Product Application



100%	25%	5-25%
4206	H500 FAST HS HARDENER	S719 THINNER*
	H600 NORMAL HS HARDENER	S711 THINNER

* recommended



18-19 s / DIN 4 mm / 20°C
Potlife: 40 minutes at 20°C



HVLP 1.6 – 1.8 mm

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.



4206 - Accelero Air dry 2K VOC Dark Grey

2-3 coats
45-50 microns/coat



THINNING RATIO%	VISCOSITY	FILM THICKNESS/COAT	3 COATS TOTAL FILM BUILD
5%	40"	70 μ	210 μ
10%	30"	67 μ	200 μ
15%	25"	65 μ	195 μ
20%	22"	60 μ	180 μ
25%	19"	55 μ	165 μ



3-5 minutes between coats

Dust free after	10 minutes @ 20 °C (68°F)
Touch free after	15 minutes @ 20 °C (68°F)
Sandable after	60 minutes @ 20 °C (68°F)



Depending on film thickness

Important note: below 15°C Do not air-dry
Low bake 5-10 minutes @ 60°C panel temperature



5-7 minutes, depending on color.
Substrate temperature 80°C-100°C (176°F to 212°F)
***Important note: keep panel at greater than 80cm from IR unit, depending on repair film thickness.**



5 Min at 60°C panel temperature (140°F)

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.



4206 - Accelero Air dry 2K VOC Dark Grey



Wear suitable protection

Product Characteristics

VOC(2004/42/EC):	2004/42/EC IIB (c) (540)540. The EU limit value for this product (product category IIB. c) in ready to use form is max 540g/ltr. The VOC content of this product in ready for use form is max.540 g/l.
Specific Gravity:	4202 (Grey) = 1.64 kg/cm ³ 4204 (White)= 1.637 kg/cm ³ 4206 (Dark Grey) = 1.493 kg/cm ³
Flash Point:	25°C (77°F)
Solid Content:	Approx. 62.5% - 67.5% by weight RFU, depending on reduction ratio.
Coverage:	8 - 9 m ² /l at 5.7-5.8 m ² /l at 80-micron film thickness (theoretical) micron dry film thickness
SDS:	Refer to the Safety Data Sheet

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.