



# S135 - Blending Additive

## Product Description

- For Blending-in Gen<sub>2</sub>O Waterborne Basecoat.
- Easy handling.
- Ready to spray.

## Product Application 1:

Blending-in Gen<sub>2</sub>O Basecoat directly over S135 Blending agent.



- Mix S135. 5:1 with Gen<sub>2</sub>O water S120.
- Spray blending area with one coat of S135 avoiding the edges
- Apply mixed Gen<sub>2</sub>O Basecoat in the wet film until covered.
- Blend-in the overlapping area with reduced air pressure (1.0-1.5 bar)



General Clearcoats.

## Product Application 2:

Blending-in Gen<sub>2</sub>O Basecoat mixed with S135 Blending agent.



- Mix Gen<sub>2</sub>O Basecoat with 50% S135 blending agent.
- Blend-in overlapping area with reduced air pressure by (1.0 – 1.5 bar)



General Clearcoats.

## Product Characteristics

### **Note:**

Occasionally it may be necessary to obtain opacity on the primed area before proceeding.

### **Cleaning the Equipment:**

Clean after use with Water.

Note: General recommends that our products not be used under 10°C. Usage below 10°C can result in extended drying times or product failure

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.