



10050 - 2K Premium Clear

Descripción:

Barniz 2K con muy buenos acabados, excelente brillo y buen cuerpo. Muy estable es superficies verticales. Puede volver a aplicar sin lijar antes de 24h.

Sustratos Aconsejables :

- “General” GenRock Basecoat.
- “General” Gen2 O Basecoat.

Product Application



100%	100%
10050	H820 2K L.E. HARDENER FAST
	H920 2K L.E. HARDENER SLOW
	H960 2K L.E. HARDENER EXTRA SLOW



19 sec / DIN 4 mm / 20 °C (68 °F)
Potlife: 5h at 20°C



Convencional: 1.3 – 1.4 mm
2.0 – 2.5 bar entrada de presión



2 capas normales 50- 60 micras por capa



Esperar 10 min antes de aumentar la temperatura
Hornear 20 min a 60°C de temperatura del panel

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.



10050 - 2K Premium Clear



8 min. Onda Corta
Mantener el aparato a 80 cm de distancia



Conveniente usar protección

	15 - 20° C.				20 - 25° C.				25 - 30° C.				+ 30° C.			
	Thinner 721				Thinner 721 - S2040				Thinner S2040				Thinner 20 40			
	Hardener	Time to sanding			Hardener	Time to sanding			Hardener	Time to sanding			Hardener	Time to sanding		
	20° C.	60° C.	IR	20° C.	60° C.	IR	20° C.	60° C.	IR	20° C.	60° C.	IR	20° C.	60° C.	IR	
Full paint	H700	OVERNIGHT	20 MINUTES	15 MINUTES	H700	OVERNIGHT	20 MINUTES	15 MINUTES	H750	OVERNIGHT	20 MINUTES	15 MINUTES	H760	OVERNIGHT	20 MINUTES	15 MINUTES
Vertical areas	H600	OVERNIGHT	20 MINUTES	15 MINUTES	H700	OVERNIGHT	20 MINUTES	15 MINUTES	H750	OVERNIGHT	20 MINUTES	15 MINUTES	H750	OVERNIGHT	20 MINUTES	15 MINUTES
Fast Repair	H200 H500	OVERNIGHT	20 MINUTES	15 MINUTES	H500 H600	OVERNIGHT	20 MINUTES	15 MINUTES	H500 H600	OVERNIGHT	20 MINUTES	15 MINUTES	H600 H700	OVERNIGHT	20 MINUTES	15 MINUTES
Soft plastics																
30 % - 810 Plasticizer	H500	OVERNIGHT	45 MINUTES	NA	H500	OVERNIGHT	45 MINUTES	NA	H600	OVERNIGHT	45 MINUTES	NA	H750	OVERNIGHT	45 MINUTES	NA
Hard plastics																
15 % - 810 Plasticizer	H500	OVERNIGHT	35 MINUTES	NA	H500	OVERNIGHT	35 MINUTES	NA	H600	OVERNIGHT	35 MINUTES	NA	H750	OVERNIGHT	35 MINUTES	NA

Características del Producto

VOC (2004/42/EC):

2004/42/IIB(d)(420)420. El valor límite de la UE para este producto (categoría de producto IIB.d) en forma lista para su uso es de 420 g/ltr como máximo. El contenido de COV de este producto en forma lista para su uso es de máx. 420 g/l.

Punto de Inflamación:

25°C

Contenido en sólidos:

52.1 % por peso listo al uso

Cubrición:

9-10 m² /l a 50 micras capa teórica

SDS:

Ver Ficha de Seguridad

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.